

ALPASE M-5

ALUMINUM MOLD PLATE

Proven Technology in AA 5083 Chemistry

M-5 APPLICATIONS

M-5 Mold Plate is used in a variety of manufacturing applications:

- Injection Molds
- Blow Molds
- Structural Foam Molds
- Rubber Molds
- Vacuum Forming Tools
- Compression Molds
- Heating and Cooling Plates
- Semi-conductor & Solar Equipment

M-5 PROPERTIES

Tensile Strength	41 ksi	Coefficient of Expansion	13.2×10^{-6} (68°-212°F)
Yield	18 ksi	Electrical Conductivity	29% (I.A.C.S)
Elongation	12%-15%	Microstructure	Vacuum Tight
Hardness	70 HB	Thermal Conductivity	81 Btu/ft h x °F
Density	.096 lb./in ³	Modulus of Elasticity	$10.3 \text{ KSI} \times 10^6$

Information provided does not imply a guarantee of properties or capability of manufacturing or use.

Surface Condition

Milled Surface Top and Bottom

Quality

M-5 plates are U/T inspected

Tolerances

Thickness +1/8" - 0"
Width/Length +1/4" - 0"

Standard Sizes

Thickness Up to 30"
Widths Up to 96"
Lengths Up to 195"



New Technologies
In Aluminum



Melinda Barraza
Inside Sales
Direct: 951-727-3183
mbarraza@tst-inc.com

Todd Massie
VP of Business Development
Cell: 860-986-9976
tmassie@tst-inc.com

13428 Benson Ave
Chino, CA 91710 USA
www.tst-inc.com

TST INC